

Specification

Floor coating IP – 1210

This special product is specially formulated for cement/brick built and mosaic made floors and will protect floor in front of push, chemicals (acid and bases, corrosive materials) abrasion and particles in the air. Another advantage of using this product is that it has magnificent adhesion property to the surface and application method is very simple. Also the surface is washable.

Major properties:

1	Color/Hue	Clear or according to the customer's need
2	Viscosity	0.3 Pa .s 10000sec $\dot{\gamma}$
3	Destiny	1.25 gr./cm ³
4	Nonvolatile materials (Weight percent)%	40.2%
5	Dry time	At least one hour in 25 degree
6	Utilization time	2~3 days after application
7	Ignition point	+44
8	Chill resistance	In –40 C after 24 Hrs. no changes seen on dry film
9	Test method	ASTM C309 and positive test results
10	Dry film thickness DFT	200 micron
11	Application method	By painting brush or roller 300-350 gr./m ² and by Airless 400-500 gr./m ²
12	Storage time	At least 1 year away from direct sun rays

Important Note:

Please note that all Sepitak's products are solvent free so these products do not need any kind of solvent or hardener. You are highly recommended not add any kind of solvent to our products.

You can wash applying appliances with thinner.